

Preparation of ZnO-CuO composite photocatalyst using the sonochemical method

by Rahadian Zainul Et.al

Submission date: 20-May-2021 09:50PM (UTC+0700)

Submission ID: 1590367525

File name: Prosiding_5_Preparation_of_ZnO.pdf (610.86K)

Word count: 2303

Character count: 12086

PAPER · OPEN ACCESS

Preparation of ZnO-CuO composite photocatalyst using the sonochemical method

To cite this article: Rahadian Zainul *et al* 2019 *J. Phys.: Conf. Ser.* **1317** 012036

View the [article online](#) for updates and enhancements.



IOP | ebooks™

Bringing you innovative digital publishing with leading voices to create your essential collection of books in STEM research.

Start exploring the collection - download the first chapter of every title for free.

Preparation of ZnO-CuO composite photocatalyst using the sonochemical method

Rahadian Zainul*, Jon Effendi, and Mashuri

Department of Chemistry, Faculty of Mathematics and Natural Science, Universitas Negeri Padang, Indonesia

*rahadianzmsiphd@yahoo.com

Abstract. This research aims to synthesize ZnO-CuO composites to be applied as a catalyst material that acts on visible light. The preparation process of ZnO-CuO composite using sonochemistry method. Precursor used in this research is Zn (CH₃COO)₂·2H₂O and CuSO₄·5H₂O with a ratio of 1: 1, 2: 1, 3: 1, 4: 1, 5: 1 and variations in the exposure time used 70, 90, 105, 120, 135 minutes. The result of the FTIR spectral characterization shows that the formation of new peak is ZnO-CuO composite wave at 400-600 nm area, with UV-DRS Obtained ZnO band gap value of ~ 3:25 eV and ZnO-CuO 2: 1 ~ 2.75 eV.

1. Introduction

The application of photocatalyst can be used to generate electricity, as reported in previous research that the CuO as the electrode on the PV-EC cell [1]. The applications of the environmental aspects are, ZnO photocatalyst is used as a sensitizer and a starter on the degradation of humic acid in peat swamp water. In photodegradation of humic acid mineralized into more simple products [2].

Semiconducting zinc oxide (ZnO) is the best alternative choice after TiO₂ in its application as a semiconductor photocatalyst [3]. As a basic consideration is the semiconductor ZnO resistant to corrosion, which has an energy gap (E_g = 3.2 to 3.5 eV), and cheaper than TiO₂. So that ZnO can be activated by UV radiation (ultraviolet), which resulted the efficiency of ZnO photocatalytic lower in visible light. Increasing of the photocatalytic activity of ZnO in visible light can be done by reducing the energy band gap ZnO by the addition of another semiconductor which having a narrow band gap. The incorporation of ZnO has been done with other metal oxides and sulfides such as TiO₂, SnO₂, WO₃, NiO, Fe₂O₃, and CuO [4-8]

Preparation of ZnO-CuO nano-composites can be done by several methods such as chemical synthesis method solids, coprecipitation, sol gel, and sonochemical (sonochemistry). Sonochemical method (Ultrasonic Irradiation) is used to synthesize ZnO-CuO Nanocomposite because it has several advantages such as the synthesis of an inexpensive, fast, easy to control the size, the reaction temperature is low and the resulting particles have a high homogeneity. Sonochemical synthesis of nanomaterials using the method performed by using ultrasonic waves [9-12].

Research will be carried out to produce ZnO-CuO composites having a high photocatalytic efficiency in the area of visible light, compared to the semiconductor ZnO and CuO.



3
Content from this work may be used under the terms of the Creative Commons Attribution 3.0 licence. Any further distribution of this work must maintain attribution to the author(s) and the title of the work, journal citation and DOI.

Published under licence by IOP Publishing Ltd

2. Tools and Materials

2.1. Tool

The tools used in this research are Spectrophotometer UV/Vis, Box photocatalyst consisting of a UV lamp and a magnetic stirrer brands Selecta Multimatic, Ultrasonic (45 Hz) brand of Ultrasonic Cleaner 968, X-Ray diffraction (XRD), Fourier Transform Infrared (FTIR), centrifuges, Oven brands Xu France Etuves, 225 Furnance (Neycraft), analytical Balance (Kern), and glassware: flask, beaker, a pipette and stir bar.

2.2. Materials

Materials research in this study are zinc acetate dihydrate $\text{Zn}(\text{CH}_3\text{COO})_2 \cdot 2\text{H}_2\text{O}$ (Merck), $\text{CuSO}_4 \cdot 5\text{H}_2\text{O}$ (Merck), KOH (Merck), ethanol, Cetyltrimethylammonium bromide (CTAB, Merck), ZnO (Merck), CuO (Merck) and distilled water.

3. Experimental

3.1. Synthesis of ZnO-CuO catalyst

Mixed 0.160 g Zn $(\text{CH}_3\text{COO})_2 \cdot 2\text{H}_2\text{O}$, $\text{CuSO}_4 \cdot 5\text{H}_2\text{O}$ 0.2497 g, 0.5611 g and 0.1093 g CTAB KOH diluted with distilled water to a volume of 30 mL solution. Then stirred for 15 minutes. The mixture is heated at a temperature 50°C and ultrasonic at a frequency of 45 Hz for one hour. The mixture was further centrifuged at a speed of 5000 rpm for 10 minutes, the filtrate was discarded. The sediment was washed with 30 mL of distilled water and 20 mL of absolute ethanol. The precipitate was oven-dried at 120 °C temperature for 2 hours. Calcined at 500°C temperature for 5 hours, by raising the temperature gradually from 200 for 30 minutes, 300 for 45 minutes, and a temperature of 400 for 60 minutes. The same procedure was performed by varying the composition ratio of precursors, namely $\text{Zn}(\text{CH}_3\text{COO})_2 \cdot 2\text{H}_2\text{O} : \text{CuSO}_4$ (2: 1, 3: 1, 4: 1, 5: 1) [13].

3.2. Characterization of ZnO-CuO Catalyst

Characterization by using UV-DRS performed to calculate the value of band gap of ZnO-CuO catalysts. Later in the characterization by FTIR instrument which aims to determine the location of the peak of the information contained in the catalyst oxide ZnO-CuO generated.

4. Results and Discussion

4.1. Characterization

4.1.1. Catalyst Characterization by Fourier Transform Infra Red (FTIR).

Characterization of ZnO-CuO use *Fourier Transform Infrared*(FTIR) aims to analyze the absorption bands of the vibrations of functional groups ZnO. The working principle of FTIR is based on the amount of absorption of light by a sample. If a sample is passed by infrared radiation, the molecules will absorb energy and there is a transition between the basic vibrational level (ground state) and the excited vibrational levels (excited state) [14].

FTIR analysis was conducted to see the vibrations of functional groups ZnO-CuO nanoparticles. Measurements were taken at a wavelength range of 400-4000 cm^{-1} . From this test result chart % Transmittance (% T) of the wavenumber (cm^{-1}). FTIR will generate absorption peaks associated with the frequency of vibration of the atoms making up the bonds of a material.

In this research, FTIR analysis done catalyst sample of pure ZnO, CuO purely as a comparison standard for catalyst samples are synthesized ZnO-CuO. FTIR spectra of ZnO-CuO catalysts can be seen in Figure 1




Figure 1. FTIR spectra of (a) ZnO, (b) CuO, (c) ZnO-CuO 1.1, (d) ZnO-CuO 2.1, (e) The ZnO-CuO 3.1, (f) the ZnO-CuO 4.1, (g) ZnO-CuO 5.1

From the results of the FTIR spectra Figure 1 shows that the catalyst synthesis of ZnO-CuO 2:1 shows that formed a new absorption band showing the stretching vibration of the metal oxide composite ZnO-CuO, while the comparison of the other isn't formed Composite ZnO-CuO but only CuO stretching vibration peaks are formed. This is because period of relative molecular greater than Cu Zn resulting in the peak of CuO. In the range of 400-600 nm wave number is stretching vibration area absorption of the metal oxide [15].

4.1.2. Band Gap Analysis of ZnO and ZnO-CuO 2: 1 with UV-DRS

Band gap analysis was performed using UV-DRS to determine the value of the band gap. The band gap is a gap between the valence band is full of electrons with an empty conduction band electrons. Values in the semiconductor band gap is very important because it affects the performance of the semiconductor in a stream of electrons and holes [16-21].

In this research, the analysis by using UV-DRS is only carried out on samples of pure ZnO-CuO and ZnO catalyst is synthesized ZnO-CuO 2:1 a sample ZnO-CuO catalysts maximum seen from the results Phototransformation LAS. Analysis of samples obtained from the relationship% Reflectance on wavelength. The data obtained will be processed to obtain estimates of the value of the band gap of each sample. which the results we got can be determined how the pure ZnO influenced with catalyst

synthesis ZnO-CuO 2:1 against the tire energy gap of each sample. Graph band gap of ZnO and ZnO-CuO 2:1 shown in Figure 2




Figure 2. Graph band gap value (a) ZnO, (b) ZnO-CuO 2: 1 by using UV-DRS.

The value of the band gap of the semiconductor can be calculated using Kubelka-Munk theory. The value of the band gap of ZnO and ZnO-CuO 2: 1 calculated from spectral reflectance Based on Figure 2, visible band gap value obtained for ZnO ~ 3.25 eV and ZnO-CuO 2: 1 ~ 2.75 eV. This shows that with the addition of another semiconductor is CuO on ZnO catalyst can lower the value of the band

gap. small band gap value obtained on ZnO-CuO 2: 1. This makes the photocatalytic activity more effective than ZnO, CuO and ZnO-CuO composite other comparisons.




Figure 3. Absorbance Spectra Catalyst namely: (a) CuO, (b) ZnO-CuO 2: 1 and ZnO of Spectrophotometer UV-DRS

From figure 3 can be seen that the Merger ZnO with CuO having a narrow band gap can reduce the band gap ZnO itself so that the absorption of ZnO shifted to the visible light region.

4.2. Conclusions

Based on this result, FTIR spectral characterization shows that the formation of new peak is ZnO-CuO composite wave at 400-600 nm area, with UV-DRS Obtained ZnO band gap value of ~ 3.25 eV and ZnO-CuO 2: 1 ~ 2.75 eV.

2 Acknowledgements

Thank you the Government of the Republic of Indonesia, Ministry of Technology, Research and Higher Education on the Research Grand of Riset Unggulan Perguruan Tinggi in 2018-2019. Special thanks to the Rector of the Universitas Negeri Padang, has been facilitated and funded for Terapan Research in 2018, and Chemical Laboratory of Universitas Negeri Padang. Thanks to the research team of UNP Chemistry undergraduate students and the Research Team from Zainul for Advanced Material Processing (ZAMP).

References

- [1] Zainul R, Alif A, Aziz H, Arief S, Dradjad S, Munaf E 2015 Design of Photovoltaic Cell with Copper Oxide Electrode by Using Indoor Lights, *Research Journal of Pharmaceutical, Biological and Chemical Sciences* 6(4) pp. 353-361
- [2] Zainul R 2016 Effect of Temperature and Particle Motion Against the Ability of ZnO Semiconductor Photocatalyst in Humic Acid *Der Pharmacia Lettre* 8 pp. 120-124
- [3] Hoffman M R, Martin S T, Choi W, Bahnemann D W 1995, *Chem. Rev.* 95 71-74, 77, 79, 82, 85-87
- [4] An T, Liu X, Hu X, Sheng G, Fu J, Zhang M 2010 Preparation of a High-Activity ZnO/TiO₂ Photocatalyst via Homogeneous Hydrolysis with Low Temperature Crystallization Method, *Materials Journal Letters* 64 1883-1886

- [5] Kowsari E, Ghezelbash M 2012 Ionic Liquid-Assisted Facile Synthesis of ZnO/SnO₂ Nanocomposites and Investigation of Their Photocatalytic Activity, *Journal of Material Letters* 68 17-20
- [6] Li B, Y.Wang Facile Synthesis and Photocatalytic Activity of ZnO-CuO Nanocomposite, *Journal of Superlattices Microstructures* 47 615-623
- [7] Dm F, W.Hechenleitner, Silva M, Lima M, Bittencourt P, R.Silva, Melo M C, Pineda E 2009 Preparation and characterization of NiO, Fe₂O₃, Ni_{0.04}Zn_{0.96}O and Fe_{0.03}Zn_{0.97}O, *Journal of Nano Materials*. 118: 447-452 118 447-452
- [8] Y. C, Kai Y, Qing S, Jimmy Y, Fangfang C, Xin L 2011 Preparation of WO₃/ZnO Composite photocatalyst and Its Photocatalytic Performance, *Chines Journal and Catalysis* 32555-565 555-565
- [9] Cash R, Birer O 2012 Shape Control of Copper Hydroxysulfates. *Journal of Ultrasound and Sonochemistry*. 19: 692-700., *Journal of Ultrasound and Sonochemistry* 19 692-700
- [10] Wongpisutpaisan N, P.Charoonsuk, N.Vittayakorn, W.Pecharapa 2011 Sonochemical Synthesis and characterization of Copper Oxide Nanoparticles, *Journal of Energy Procedia* 9 404-409
- [11] Wei Y, Chang P 2008 Characteristics of Nano Zinc Oxide Synthesized Under Ultrasonic Condition, *Journal of Physics and Chemistry of Solids* 69 688-692
- [12] Xiao Q, Huang S, J.Zhang, C.Xiao, X.Tan 2008 Sonochemical Synthesis of ZnO Nanosheet, *Journal of Alloy Compound* 459 L18-L22
- [13] Kasuma N Y 2012 Use of Composite ZnO-Cuo was Synthesized by Sonochemistry Used as Catalysts for Photodegradation Methyl Orange and Antibacterial Substances, *Thesis. Padang: State University of Andalas*
- [14] Puspitasari P 2012 Synthesis and Characterization of Bentonite Tasikmalaya organoclay intercalated with non-ionic surfactant Triton X-100: Variation Cation Balancing, *Essay. Depok : Universitas Indonesia*
- [15] Nakamoto K 1997 Infrared and Raman Spectra of Inorganic and Coordination Compounds. 5th Edition, *John and Sons, Inc. Canada Nasikin*
- [16] Lestari D 2011 Preparation of Nanocomposite ZnO/TiO₂ with Sonochemical and Test Methods The Activities to Photodegradation Phenol, *Thesis Faculty of Mathematics and Natural Sciences. Semarang State University*
- [17] Zainul R 2016 Design and Modification of Copper Oxide Electrodes for Improving Conversion Coefficient Indoor Lights (PV-Cell) Photocells *Der Pharma Chemica* 8 pp. 388-395
- [18] Zainul R, Alif A, Aziz H, Arief S 2015 Disain Geometri Reaktor Fotosel Cahaya Ruang, *Jurnal Riset Kimia* 8 131-142
- [19] Zainul R, Alif A, Aziz H, Arief S, Darajat S 2015 Modifikasi dan Karakteristik I-V Sel Fotovoltaik Cu₂O/Cu-Gel Na₂SO₄ Melalui Iluminasi Lampu Neon, *Eksakta Berkala Ilmiah Bidang MIPA* 15 50-56
- [20] Zainul R, Alif A, Aziz H, Yasthopi A, Arief S, Syukri 2015 Photoelectrospitting Water for Hydrogen Production Using Illumination of Indoor Lights, *Journal of Chemical and Pharmaceutical Research* 7(11) pp. 57-67
- [21] Zainul R, Oktavia B, Dewata I, Efendi J 2018 Thermal and Surface Evaluation on The Process of Forming a Cu₂O/CuO Semiconductor Photocatalyst on a Thin Copper Plate, *IOP Conference Series: Materials Science and Engineering* 335 012039

Preparation of ZnO-CuO composite photocatalyst using the sonochemical method

ORIGINALITY REPORT

13%

SIMILARITY INDEX

8%

INTERNET SOURCES

13%

PUBLICATIONS

9%

STUDENT PAPERS

PRIMARY SOURCES

1

Submitted to Universitas Pendidikan Ganesha

Student Paper

6%

2

R Zainul, I Dewata, B Oktavia. "Fabrication of hexagonal photoreactor indoor lights", Journal of Physics: Conference Series, 2019

Publication

4%

3

docplayer.net

Internet Source

3%

Exclude quotes On

Exclude bibliography On

Exclude matches < 50 words